

Wording to assist in writing a specification for Austral Plywoods plywood products

AUSTRAL EXTERIOR to be used/installed as specified.

Plywood to be manufactured with timber species: **Araucaria (Hoop Pine)**.

Face and back veneer grades to be **AC**, conforming to Australian Standards for veneer grading.

Core grade to be **D**, conforming to Australian Standards for veneer grading.

Glue system to be used is **A-Bond Phenolic (black glueline)** with formaldehyde emissions rating of **Super E0**, tested in accordance with AS/NZS 2098.11 : 2005. Manufacturer warranty on glue bond to be **25** years.

Plywood supplied must be manufactured to Australian Standard **AS/NZS 2271:2004** and be certified under the **EWPA JAS-ANZ** Product Certification Scheme. Plywood must also be Green Star rated and be environmentally certified to **RW/PEFC**.

Plywood to be certified Fire Group **3** per BCA Specification C1.10 clause 4.

Panel size to be **2400 x 1200, 2700 x 1200mm** (delete as required).

Panel thickness to be **1.5, 3, 4, 5, 6.5, 9.5, 12.5, 16, 19, 25, 32mm** (delete as required).

<http://www.australply.com.au/austral-exterior>

Contact: Austral Plywoods Sales - sales@australply.com.au - 07 34268666



**AUSTRAL
PLYWOODS**

07 3426 8666
sales@australply.com.au
www.australply.com.au

*100% Australian
made, since 1925*